

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵: C08J 9/00	A1	(11) International Publication Number: WO 94/22943 (43) International Publication Date: 13 October 1994 (13.10.94)
(21) International Application Number: PCT/US94/03545 (22) International Filing Date: 31 March 1994 (31.03.94) (30) Priority Data: 08/041,503 1 April 1993 (01.04.93) US (71) Applicant: THE REGENTS OF THE UNIVERSITY OF CALIFORNIA [US/US]; 22nd floor, 300 Lakeside Drive, Oakland, CA 94612 (US). (72) Inventors: MAYER, Steven, T.; 16026 Selborne Drive, San Leandro, CA 94578 (US). KASCHMITTER, James, L.; 6921 Alisal Street, Pleasanton, CA 94566 (US). PEKALA, Richard, W.; 802 Cliffside Drive, Pleasant Hill, CA 94523 (US). (74) Agent: SARTORIO, Henry, P.; P.O. Box 808, Livermore, CA 94550 (US).		(81) Designated States: CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: METHOD OF LOW PRESSURE AND/OR EVAPORATIVE DRYING OF AEROGEL (57) Abstract A process whereby Resorcinol/Formaldehyde (RF) aerogel having a density of about 0.4-1.2 g/cc can be manufactured using a simple air drying procedure. This process is inherently simpler, quicker, and less expensive than the more conventional supercritical or subcritical CO ₂ extraction procedures. RF aerogels can be used as produced, such as in insulation applications, or pyrolyzed to form carbon aerogels with a density of about 0.9 g/cc for use in applications such as batteries, supercapacitors, etc.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

METHOD OF LOW PRESSURE
AND/OR EVAPORATIVE DRYING OF AEROGEL

The United States Government has rights in this invention pursuant to Contract No. W-7405-ENG-48 between the United States Department of Energy and the University of California for the operation of Lawrence Livermore National Laboratory.

BACKGROUND OF THE INVENTION

The present invention relates to organic aerogels, particularly to a method of fabricating organic aerogels having a density of about 0.4-1.2g/cc, and more particularly to a process whereby organic aerogels, such as resorcinol-formaldehyde aerogels, can be manufactured using a simple air drying procedure.

Foamed organic polymers and organic foam composite materials having relatively low densities are well known and are used in the insulation, construction, and similar industries. Also, machinable and structurally stable, low density (~0.04g/cc), micro-cellular (~15 microns) carbon, and catalytically impregnated carbon foams are known, as exemplified by U.S. Patent No. 4,756,898 issued July 12, 1988 to R.W. Hopper et al. In addition, electrically conductive open-celled, micro cellular (1-50 microns), carbon foam having a density range of 0.1-1.0g/cc have been developed, as exemplified by U.S. Patent No. 4,832,870 issued May 23, 1989 to R.L. Clough et al. Further, low density (0.05-0.07g/cc), micro cellular (<10 microns), foams have been fabricated for use in inertial confinement fusion targets, as exemplified by U.S. Patent No. 4,832,881 issued May 23, 1989 to C.A. Arnold, Jr. et al.

Development efforts have also been directed to low density organic aerogels which may be carbonized to form low density (≤ 0.1 g/cc) carbon aerogels with a cell size of less than 0.1 micron for use in high-energy physics applications, adsorption of toxic gases, ion exchanger/and as a catalyst support, etc., as exemplified by U.S. Patents No. 4,873,218

- 2 -

issued October 10, 1989 and No. 4,997,804 issued March 5, 1991, each to R.W. Pekala, and paper UCRL-99846, Resorcinol-Formaldehyde Aerogels And Their Carbonized Derivatives, R.W. Pekala et al., dated October 24, 1988. Low and high density carbon foams of this type have also been utilized in super capacitor applications, as described and claimed in Applicants' copending U.S. Patent Application Serial No. 07/822,438, filed January 17, 1992, entitled "Supercapacitors Based On Carbon Foams".

While aerogel or foam technology and the potential uses thereof have been extensively described in the art, one of the major technical challenges has been to develop a low cost method of producing aerogel materials, whatever the end use. Most of the cost and a large fraction of the processing time of organic aerogels, their carbonized derivatives, and other carbon foams is associated with the drying of the polymeric gel precursors. In the case of aerogels, supercritical drying is the established technique for removing the solvent from the pores of the gel. In an effort to resolve this problem, a method of subcritical drying of polymeric foams, such as resorcinol/formaldehyde (RF) aerogels, has been developed which potentially will substantially lower the capital equipment and processing costs associated with aerogel or foam production (due to the lower required pressures). This new drying procedure is set forth hereinafter in a process for the production of aerogels using a simple evaporative drying procedure.

SUMMARY OF THE INVENTION

It is an object of the present invention to provide simplified process for producing organic aerogels and their carbonized derivatives.

A further object of the invention is to provide an aerogel fabrication process which reduces processing time and lowers capital equipment and processing costs associated with foam production.

Another object of the invention is to provide a process for the production of aerogels using a simple evaporative drying procedure.

Another object of the invention is to provide an organic aerogel or a carbonized aerogel having a density of about 0.4-1.2g/cc, for use in thermal or acoustic insulation or in rechargeable batteries, supercapacitors, etc.

- 3 -

Another object of the invention is to provide a simplified process using an evaporative drying procedure for producing carbonized aerogels having a density of 0.4-1.2g/cc.

Other objects and advantages of the present invention will become apparent from the following description. The foregoing and other objects of this invention are accomplished by reducing the processing time and equipment costs in the fabrication of organic aerogels and other carbon foams associated with the drying of the polymeric gel precursor. This invention utilizes a simple evaporative drying procedure rather than conventional supercritical or subcritical CO₂ extraction procedures. In verifying this invention resorcinol/formaldehyde carbon aerogels having a density of 0.4-1.2g/cc were produced.

DETAILED DESCRIPTION OF THE INVENTION

The invention is directed to a process for producing organic aerogels or their carbonized derivatives or foams using a drying procedure which is inherently simpler, quicker, and less expensive than the conventional supercritical or subcritical CO₂ extraction procedures. The term aerogel refers to both inorganic (silica) and organic (carbon) aerogels. This invention is directed only to organic based aerogels and foams. Carbon aerogel is one type of organic foam. This technique has so far only been experimentally verified using resorcinol/formaldehyde (RF) carbon aerogels, but other types of organic aerogels can be produced. The process of this invention involves a simple air drying procedure, and the aerogels so produced can be used as produced or pyrolyzed to form a carbon aerogel, depending on the desired use thereof.

The improved drying procedure of the invention is described hereinafter in detail with respect to the fabrication of intermediate density (~0.6g/cc) resorcinol/formaldehyde (RF) aerogels. The resultant 0.6g/cc RF aerogel is then pyrolyzed to produce a carbon aerogel having a density of about 0.9g/cc. Also, while low density (≤ 0.01 mg/cc), resorcinol/formaldehyde (RF) aerogels having ultra-fine cell or pore size have been previously developed, as exemplified by above-referenced U.S. Patents No. 4,873,218 and No. 4,997,804 issued to R.W. Pekala, coinventor of this invention, the RF aerogel produced by the following description of the present invention is of an intermediate density (~0.6g/cc).

- 4 -

In carrying out a process for verifying the air drying procedure of this invention, intermediate density RF aerogels were produced by the following operational sequence:

1. 12.35g of resorcinol and 17.91g of 37% formaldehyde were mixed with 5.6g of 0.1M Na_2CO_3 (sodium carbonate) in a glass beaker, for example. Note that in this formulation, no additional water other than that from the formaldehyde or sodium carbonate is used.

2. This mixture was poured into glass vials, sealed, and subsequently cured at room temperature for one (1) day.

3. The gel is then further cured at 50°C for one day, and then at 90°C for at least an additional day.

4. The thus formed "aquagel" was then removed from the glass beaker and sliced using a diamond blade saw to produce thin wafers approximately 0.050 inch in thickness.

5. The thus produced wafers were placed in a solvent of acetone, and the acetone was exchanged several times to insure that all of the water had been removed from the pores of the wafers. This process took several (about four) hours.

6. Next, cyclohexane was exchanged for the solvent (acetone) in the wafers in a similar manner as directly above described. This process took several hours.

7. The cyclohexane in the pores of the RF gel wafers was allowed to slowly evaporate in air inside a hood with the wafers placed upright (on edge) so that both sides were exposed to the air, and able to evaporate (dry) at comparable rates. The drying procedure took about 2-3 hours at a temperature of about 20-50°C. The drying time will vary due to air flow rate and temperature.

If desired, to promote additional cross-linking of the gels, during the initial water to solvent (acetone) exchange, a concentration of ≤ 0.1 wt.% of trifluoroacetic acid may be added to the solvent. Also, if desired, the wafers may be air dried at low pressure (approximately 0.1-1.0 atmosphere) or within an evacuated chamber or vacuum oven. Also, after drying, the wafers can be cut, chopped, or sectioned into any desired shape or ground to produce particles of desired sizes.

During the drying procedure, the diameter of the wafers decreased slightly (from 0.925 inch to approximately 0.90 inch) and the wafer properties were consistent with conventional RF aerogels

- 5 -

properties (sticky to the touch and red translucent in color). Certain of the wafers, prepared in the manner described above, were then pyrolysed in an inert (nitrogen) atmosphere at 1050°C for a time period of 4 hours to form a carbonized aerogel (carbon foam). The wafers had a density of about 0.6g/cc prior to carbonization and a density after carbonization of about 0.9g/cc.

The carbon aerogel samples were placed into 5M KOH (potassium hydroxide) and capacitance measurements were made, with the results indicating a capacitance of about 19F/cc when the electrodes are charged to a 1 volt potential difference, thus establishing a use capability, such as in double layer capacitors (super-capacitor) as described and claimed in above-referenced U.S. Application S.N. 07/822,438.

The RF aerogel or carbon aerogel made in accordance with the present invention provides an intermediate density foam which may be used in its non-pyrolysed or non-carbonized form in thermal or acoustic insulation for example, and in its pyrolysed or carbonized form rechargeable batteries, supercapacitors, fuel cells, and chemical sensors, for example. By way of comparison, the drying time of the present invention is in hours compared to days required in the process of above-referenced U.S. Patents No. 4,873,218 and No. 4,997,804, for example. In addition, the air drying equipment costs of this invention are significantly less than required for the critical point drying procedure of these same two referenced patents, for example. Thus, it has been shown that the present air drying procedure results in an aerogel fabrication process which is simpler, quicker, and less expensive than the prior known drying procedures. Therefore, this invention provides a solution to the major technical challenge of producing low cost aerogel materials.

While a specific RF aerogel formulation has been exemplified above, other formations are possible, depending on the desired properties of the user. The process in general requires that the reactants are mixed with a catalyst. The reactants (phenolic monomers) include resorcinol, phenol, catechol, phloroglucinol, and other polyhydroxy-benzene compounds that react in the appropriate ratio with formaldehyde or furfural in the presence of catalytic amounts of a base catalyst, such as sodium carbonate (Na_2CO_3) lithium carbonate (Li_2CO_3), and potassium carbonate (K_2CO_3), for example. In addition to

- 6 -

resorcinol-formaldehyde, exemplified above, preferred combinations of reactants include resorcinol-furfural, phenol-resorcinol-formaldehyde, catechol-formaldehyde, and phloroglucinol-formaldehyde. Also, in addition to acetone, other solvents that may be used include methanol, isopropanol, and amyl acetate. While the above example, utilized a pyrolyzing temperature of 1050°C, pyrolyzing may be carried out in a temperature range of about 500-3000°C, depending on the materials, etc. involved.

While a specific example of a process utilizing the air drying procedure has been set forth, with specific materials, quantities, times, parameters, etc., set forth, such is not intended to limit the invention to the specific described process, since other process may effectively utilize the air drying procedure. Modifications and changes will become apparent to those skilled in the art and such are intended to be covered by the scope of this invention, which is to be limited only by the scope of the appended claims.

CLAIMS

1. In a process for producing organic aerogels, the improvement comprising the step of:
extracting the fluid from the pores of the aerogel by air drying.
2. The improvement of Claim 1, additionally including the step of positioning the aerogel material such that opposite surfaces thereof are exposed to the air so as to enable comparable drying rates of the opposite surfaces.
3. The improvement of Claim 3, additionally including the step of forming the aerogel precursor to be dried by:
forming a mixture of reactants in a solvent;
allowing the thus formed mixture to gel;
curing the thus formed gel to increase the cross-linking density;
exchanging the pore fluid in the gel with a selected solvent;
and
allowing the selected solvent to evaporate during the air drying step, thereby forming an aerogel.
4. The improvement of Claim 3, wherein the step of forming the mixture is carried out by at least mixing a monomer selected from the group consisting of resorcinol, phenol, catechol, phloroglucinol, and other polyhydroxybenzene compounds, with either formaldehyde or furfural in the presence of a base catalyst selected from the group of sodium carbonate, lithium carbonate, and potassium carbonate.

- 8 -

5. The improvement of Claim 3, wherein the step of forming the mixture is carried out by mixing resorcinol, formaldehyde, and sodium carbonate in selected proportions.

6. The improvement of Claim 5, wherein the step of curing is carried out at room temperature for a first period of time, at 50°C for a second time period, and then at 90°C for a third time period.

7. The improvement of Claim 6, wherein the step of exchanging the pore fluid with a selected solvent is carried out by exchanging the fluid with acetone, and then exchanging the acetone with cyclohexane.

8. The improvement of Claim 1, additionally including the step of pyrolyzing the thus dried aerogel in an inert atmosphere to form a carbonized aerogel.

9. The improvement of Claim 8, wherein the atmosphere is nitrogen, and wherein the step of pyrolyzing is carried out at a temperature of 1050°C.

10. The improvement of Claim 9, wherein the organic aerogel is a resorcinol/formaldehyde aerogel.

11. A method for producing an aerogel having a density in the range of 0.4-1.2g/cc, comprising the steps of:

forming a mixture of a polymeric material with a solvent;
allowing the mixture to gel while minimizing any evaporation;

curing the thus gelled mixture to form an aquagel;
exchanging water in the aquagel with a selected solvent;
allowing the selected solvent to at least partially evaporate;

and

air drying to form an aerogel.

- 9 -

12. The method of Claim 11, additionally including the step of pyrolyzing the thus formed aerogel in an inert atmosphere to produce a carbonized aerogel.

13. The method of Claim 12, wherein the step of pyrolyzing is carried out at a temperature of 1050°C.

14. The method of Claim 13, wherein the inert atmosphere is formed of nitrogen.

15. The method of Claim 12, wherein the thus produced carbonized aerogel has a density of about 0.9g/cc.

16. The method of Claim 11, wherein the step of forming the mixture is carried out by mixing resorcinol, formaldehyde, and sodium carbonate in selected proportions.

17. The method of Claim 16, wherein the step of curing the thus gelled mixture is carried out at room temperature for a specified time, at 50°C for a specified time, and then at 90°C for a specified time.

18. The method of Claim 17, additionally including the step of forming selected size pieces of the aerogel by cutting the thus formed aerogel so as to form pieces of a selected size and thickness.

19. The method of Claim 17, wherein the step of exchanging water with a selected solvent is carried out by exchanging the water with acetone and then exchanging the acetone with cyclohexane.

20. The method of Claim 19, additionally including the step of positioning the formed aerogel such that opposite surfaces thereof are exposed to the air to provide comparable drying rates of the opposite surfaces.

21. The method of Claim 11, wherein the step of air drying is carried out at a pressure of about 0.1-1.0 atmosphere.

- 10 -

22. The method of Claim 11, wherein the step of air drying is carried out following the step of solvent exchanging.

23. A resorcinol/formaldehyde aerogel produced by the method of Claim 20, and having a density of about 0.6g/cc.

24. A carbonized aerogel produced by the method of Claim 12, and having a density of about 0.9g/cc.

25. The improvement of Claim 1, additionally including the step of forming the thus produced aerogel in a desired configuration, which step of forming may be carried out prior to or after the air drying step.

26. The improvement of Claim 6, wherein the step of exchanging the pore fluid with a selected solvent is carried out by exchanging the fluid with acetone, followed by evaporation and air drying, thereby forming the aerogel.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US94/03545

A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) :C08J 9/00

US CL :521/113, 114, 181, 64; 502/418, 437

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 521/113, 114, 181, 64; 502/418, 437

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

APS: aerogel# and air and (dried or drying or dry) and pore# and extract#### and (fluid# or liquid#)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X, P	US, A, 5,252,620 (ELLIOTT, JR. ET AL.) 12 OCTOBER 1993, column 7, line 15 and line 67.	1
Y	US, A, 4,873,218 (PEKALA) 10 OCTOBER 1989, column 7, line 30.	15, 23, 24

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

Special categories of cited documents:	
A document defining the general state of the art which is not considered to be part of particular relevance	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
E earlier document published on or after the international filing date	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
O document referring to an oral disclosure, use, exhibition or other means	*A* document member of the same patent family
P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

16 MAY 1994

Date of mailing of the international search report

07 JUN 1994

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Authorized officer

DUC TRUONG

Facsimile No. (703) 305-3230

Telephone No. (703) 308-2351